

This website uses cookies to improve the user's experience during working with our network and to provide users with dedicated services and functions. By further use you agree with that.OKDetails

Adresse	Xi'an Aofa OptoelectronicsTech. Faraday Rotator/Magneto-Optic Glass No.126, Jin Hua North Road 710032 Xi'an
Pays	République du Peuple Chine

PRODUITS OU MACHINES

Faraday Roatator Glass is widely used especially in high-power optical rotator and isolator with large aperture, circulators,switches,polarimeters,magneto-optics sensor,high-power laser systems and other wanted Faraday Effect,etc. The main products as follow,please see Faraday Roatator Glass is widely used especially in high-power optical rotator and isolator with large aperture, circulators,switches,polarimeters,magneto-optics sensor,high-power laser systems and other wanted Faraday Effect,etc.

The main products as follow,please see Product Catalog for details.

* Diamagnetic Faraday Rotator Glass.Type MR1 with very important properties, its high Verdet constant 0.071~0.075min/Oe*cm at 632.8nm,it's independent of temperature from -50°~+135° with better thermal stability and widely used in magneto optical sensor and Magnetic-Optical Current Transducer (MOCT), etc.

* Paramagnetism Faraday Rotator Glass/Magneto-Optical Glasses

Type MR3-2, Verdet constant -0.329 min/Oe-cm at 632.8nm or -95.7 rad/T*m at 632.8 nm

Type MR3, Verdet constant -0.34 min/Oe-cm at 632.8nm or -98.9 rad/T*m at 632.8 nm

Type MR4, Verdet constant -0.38 min/Oe-cm at 632.8nm or -110 rad/T*m at 632.8 nm

MR3 and MR4 are the highest Verdet constant in the market available exclusively from XAOT

* Faraday Rotators Rods with high sensitive and steady which are used for all kinds of magneto optical device and instruments.

Product Description

Faraday Rotator Glass / Magneto Optical Glass

Since glass material in high power laser system is damaged as a consequence of self-focusing,low non-linear refractive index as well as high Verdet constant are important factors for Magneto-Optical Glass

Our world-leading Magneto Optical Glass with very high Verdet factor,we supply them with the shape or size of your choice

Very large plates/disks/rods from diameter 1.00 mm to 300 mm are available

Faraday Rotator Glass / Magnetic Optical Glass mainly used in faraday rotating components,fabricating optics-isolators,faraday rotators,circulators,magneto-optical modulators,optical switchs,interleavers,laser gyroscopes,goniometric devices magneto-optic storage and optical information process system,current measuring transducers for magnetic field measuring and high-voltage transmission line,new generation current sensors,wave guides, iatrolgy,spaceflight control,satellite survey and other functional devices

Faraday Rotator Glass is made with more advanced technologies,so is performance stabilization,sensitive, and inherently immune to interfere.In comparison with artificial crystal,it is inexpensive and easy to get big size block,it has been made into different types of optical fibers,so it's widely used in many fields

Specifications

The Properties of MR3-2 Faraday Rotator Glass / Magneto-Optical Glass

At 20 ° temperature

Verdet Constant -0.329min/Oe*cm or -95.7rad/T*m at 632.8 nm

Verdet Constant -0.108 min/Oe-cm or -31.4 rad/T*m at 1064 nm

Transmission window:400nm-1600nm

Refractive indices

ND=1.7441
Nd=1.7442
NF=1.7544
Nc=1.7400
N1064=1.7178

Optical Quality(Δn) /cm < 1×10^{-6} .

Abbe number:

VD=51.7
Vd=51.0

Nonlinear refractive index n_2 ($\times 10^{-13}$ e.s.u.)=2.74

Figure of merit V632.8 (nd/n_2)=0.62

Density (g/cm³):4.92

Transformation temperature Tg: 788°

Sag temperature Ts: 824°

Coeff.of linear thermal expansion:

0 - 300° ($10^{-7}/^\circ$)=62.6

100 - 300° ($10^{-7}/^\circ$)=68.2

Transparence rate T% $\geq$ 86% (Uncoated)

Transparence rate T% $\geq$ 98% (Coated)

Absorption coefficients < 0.002/cm at 1064nm.

Thermal conductivity=48.10/ °(0-100 °)

dv/dt=0.0016(0-40 °)

dv/dt=0.0006(40-80°)

Bulk laser<

Company Profile of **Xi'an Aofa OptoelectronicsTech.**

A service of glasssglobal.com, an affiliate of glasssglobal group.

Les informations publiées sur ce document sont soumises au droit d'auteur et appartiennent à la société en question resp. à la source des adresses. Tous les droits sont réservés expressément. N'importe quel utilisateur qui accède à un tel matériel peut faire ainsi seulement pour sa propre utilisation personnelle, et l'usage d'un tel matériel est au risque unique de l'utilisateur. La redistribution ou toute autre exploitation commerciale des adresses est expressément interdite. Là où une adresse est fournie par un tiers, chaque utilisateur accepte d'observer et être lié par les limites spécifiques de l'utilisation. Glass Global ne représente ou n'approuve pas l'exactitude ou la fiabilité d'aucune des informations citées dans les adresses ou pages externes auxquelles l'on se réfère ici. www.glasssglobal.com - The International Portal to the Glass Industry - OGIS GmbH